

Theory of Stress-Strain Relations in Anisotropic Viscoelasticity and Relaxation Phenomena

M. A. BIOT

Reprinted from JOURNAL OF APPLIED PHYSICS, Vol. 25, No. 11, pp. 1385-1391, November, 1954

Theory of Stress-Strain Relations in Anisotropic Viscoelasticity and Relaxation Phenomena

M. A. BIOT*

Shell Development Company, New York, New York

(Received March 19, 1954)

A thermodynamic derivation is given for the representation of a system having viscoelastic or relaxation properties by means of a potential and dissipation function familiar in Lagrangian mechanics. This leads to modes of relaxation which are used as normal coordinates to derive general expressions for operational tensors relating stress and strain. A large variety of phenomena involving interaction of diffusion, chemical reaction, heat transfer, mechanical deformation, etc., is included in this theory.

I. INTRODUCTION

THE behavior of systems having both elasticity and viscosity under applied forces or exhibiting relaxation is usually analyzed by considering a simple mechanical model constituted by interconnected springs and dashpots. An arbitrary system of this type made up of a lattice of points connected by such springs and dashpots may be considered as an n degree of freedom system which is defined by two quadratic forms, the potential energy and the dissipation function. It is first shown in Sec. II by applying Onsager's theorem and the thermodynamics of irreversible phenomena that this model may represent the behavior of a very wide variety of phenomena in the process of their response to external action in the vicinity of equilibrium. Such phenomena may involve the application of external stresses, chemical reactions due to departure from chemical equilibrium, heat transfer, etc., and the coupling between these phenomena. The present treatment therefore includes Zener's theory of thermoelastic damping as a particular case. Also included are the effects of a liquid solvent which have been found experimentally in rock creep tests. We show that we may extend the concepts of potential energy and dissipation function to cover all these cases leading to their treatment by the methods of Lagrangian mechanics.

Section III derives the existence of modes of relaxation, i.e., solutions for which all variables are proportional to a decreasing real exponential of time. Properties of decay constants and other properties of these modes such as orthogonality are examined. Use of these modes is made in Sec. IV in order to solve for the forces or external actions in terms of a limited number of external or observed coordinates, and it is found that the most general behavior of external coordinates may be represented by a model made of a number of Maxwell type materials plus a spring and a dashpot all in parallel.

Section V deals with the stress-strain relations of a continuum and introduces the concept of operational tensor as a generalization for the elastic moduli of the theory of elasticity.

Section VI deals with the particular form of these tensors for special cases of symmetry of the material. The possibility of multiple symmetry in the same material depending on the strain rate is pointed out.

The results are also applicable to electric network theory and give expression for the direct and cross-impedances of a $2k$ terminal RC network. Extension to an LC network is also quite straightforward as it amounts to replacing p by p^2 .

II. THERMODYNAMIC DERIVATION OF THE FUNDAMENTAL EQUATION OF RELAXATION PHENOMENA

We consider a general thermodynamic system with n degrees of freedom defined by n state variables q_i . These degrees of freedom are of a quite general nature. They may include coordinates, local temperatures, piezoelectric charges, concentrations such as induced by chemical or solubility processes, etc. Correlatively we assume that the system is under the action of external forces in the generalized sense denoted by Q_i such that $Q_i dq_i$ represents the energy furnished to the system. These forces may be externally applied stresses, electromotive forces, or may result from deviations of Gibbs and chemical potential from the equilibrium state. No external forces are associated with the temperature variables.

We also assume the system to be linear, i.e., that the coordinates q_i and their derivatives are linear functions of the forces Q_i . The system includes a large reservoir at a constant temperature T and the total system is closed, i.e., exchanges no heat with the outside. Under those circumstances the entropy and the internal energy are quadratic functions of the state variables.

We define the zero level of the entropy for the state where all variables are zero and T is the uniform temperature of this equilibrium state. Part of the state variables will be local temperature increments concentration increments, etc. Where no forces are applied, the entropy of the system in the vicinity of the zero level is a maximum and we may write

$$TS = -\frac{1}{2} \sum_{ij} a_{ij} q_i q_j = -V, \quad (2.1)$$

where V is a positive definite quadratic form. The

* Consultant.

constant temperature T is introduced here as a factor simply for convenience. When forces are applied this is replaced by

$$TS = -\frac{1}{2} \sum_{ij} a_{ij} q_i q_j + \sum_i \beta_i q_i. \quad (2.2)$$

If the system is displaced from the zero level by applying the forces very slowly so that the system is displaced reversibly by a succession of equilibrium states, expression (2.2) would constantly satisfy the conditions that the entropy is a maximum, namely,

$$\partial S / \partial q_i = 0. \quad (2.3)$$

We now investigate the significance of the linear terms in expression (2.2) for the entropy. We separate the system into two parts, a system I to which the forces Q_i are applied and a system II constituted by the large reservoir at the constant temperature T . Conservation of energy requires that the total heat absorbed by system I is

$$dh = dU_I - \sum_i Q_i dq_i, \quad (2.4)$$

where U_I is the internal energy of I. Hence the reservoir acquires an increment of entropy

$$dS_{II} = -\frac{dU_I}{T} + \sum_i \frac{Q_i dq_i}{T}. \quad (2.5)$$

Denoting by S_I the entropy of system I we have for the total entropy

$$dS = dS_I - \frac{dU_I}{T} + \sum_i \frac{Q_i dq_i}{T}. \quad (2.6)$$

Now in the vicinity of the origin $q_i = 0$, for a reversible process in which the forces Q_i are constantly in equilibrium with the system, we have

$$dS_I = \frac{dU_I}{T} - \sum_i Q_i dq_i. \quad (2.7)$$

But at the origin equilibrium requires $Q_i = 0$ by definition, hence at the origin

$$dS_I = \frac{dU_I}{T}. \quad (2.8)$$

We conclude for $q_i = 0$,

$$T \frac{\partial S}{\partial q_i} = Q_i = \beta_i. \quad (2.9)$$

Expression (2.2) for the total entropy becomes

$$TS = -\frac{1}{2} \sum_{ij} a_{ij} q_i q_j + \sum_i \beta_i q_i. \quad (2.10)$$

By putting equal to zero the derivatives $\partial S / \partial q_i$ we obtain n linear relations between the forces and the

coordinates which correspond to equilibrium conditions of the system under those forces.

We now apply Onsager's theorem¹ to expression (2.10). This theorem is concerned with the case where the derivatives $\partial S / \partial q_i$ are not zero, i.e., where we have a departure from equilibrium. These derivatives are considered as forces associated with time rates of change of the state variables q_i . The theorem states that these rates are linear functions of these derivatives and that the coefficients constitute a symmetric matrix. We write

$$T \frac{\partial S}{\partial q_i} = \frac{1}{2} \sum_j b_{ij} \dot{q}_j \quad (2.11)$$

with $b_{ij} = b_{ji}$. Since

$$T \sum_i \frac{\partial S}{\partial q_i} \dot{q}_i = \frac{1}{2} \sum_{ij} b_{ij} \dot{q}_i \dot{q}_j = D \quad (2.12)$$

is proportional to the rate of change of entropy which is always positive, we conclude that the quadratic form D is positive definite.

The fundamental relation between forces and state variables may therefore be written in the general form,

$$\sum_j a_{ij} q_j + \sum_j b_{ij} \dot{q}_j = Q_i. \quad (2.13)$$

These equations may also be written in the familiar Lagrangian form

$$\frac{\partial V}{\partial q_i} + \frac{\partial D}{\partial \dot{q}_i} = Q_i \quad (2.14)$$

We see that V plays the role of a potential energy and D that of a dissipation function. The system therefore is represented by a mechanical model of springs and dashpots connecting two by two a lattice of $n/3$ spacially distributed points with n independent coordinates and corresponding forces Q_i applied at these points. For simplicity we shall refer hereafter to the state variables q_i as coordinates.

III. RELAXATION MODES AND RELAXATION SPECTRUM

The general equations (2.13) are written for convenience

$$\sum_j A_{ij} q_j = Q_i \quad (3.1)$$

with

$$A_{ij} = a_{ij} + p b_{ij} \quad (3.2)$$

and the time operator

$$p = d/dt. \quad (3.3)$$

For studying the properties of these equations it is

¹ S. R. De Groot, *Thermodynamics of Irreversible Processes* (Interscience Publishers Inc., New York, 1952).

important to treat first the homogeneous equations

$$\sum_j A_{ij} q_j = 0. \quad (3.4)$$

If p is considered as a parameter we see that the homogeneous equations lead to an eigenvalue problem. An algebraic equating for the characteristic values of p is obtained by equating to zero the determinant of the coefficients A_{ij} ,

$$\Delta = \det(A_{ij}) = 0. \quad (3.5)$$

For the sake of generality we shall say that this equation is of the n th degree and that there are n roots but will consider that in addition to possible multiple and zero roots some of the roots may be infinite. We denote the roots of equation (3.5) by $-\lambda_s$. Let us assume first that the roots are all distinct, finite, and different from zero. The general solution of the homogeneous Eqs. (3.4) is then

$$q_j = \sum_s \phi_j^{(s)} e^{-\lambda_s t}. \quad (3.6)$$

To each root $-\lambda_s$ corresponds a solution

$$q_j^{(s)} = \phi_j^{(s)} e^{-\lambda_s t} \quad (3.7)$$

which is called a relaxation mode. That the roots $-\lambda_s$ are real and negative is easily seen as follows. We consider two modes

$$\begin{aligned} q_j^{(s)} &= \phi_j^{(s)} e^{-\lambda_s t}, \\ q_j^{(r)} &= \phi_j^{(r)} e^{-\lambda_r t} \end{aligned} \quad (3.8)$$

corresponding to the two roots $-\lambda_s, -\lambda_r$. That these solutions are orthogonal is established by the usual procedure of substituting each solution in the equation then multiplying each equation for the solutions $\phi_j^{(s)}$ by $\phi_i^{(r)}$ and those for $\phi_j^{(r)}$ by $\phi_i^{(s)}$. Adding each set of equations gives the two relations

$$\sum_{ij} a_{ij} \phi_j^{(s)} \phi_i^{(r)} - \lambda_s \sum_{ij} b_{ij} \phi_j^{(s)} \phi_i^{(r)} = 0, \quad (3.9)$$

$$\sum_{ij} a_{ij} \phi_j^{(r)} \phi_i^{(s)} - \lambda_r \sum_{ij} b_{ij} \phi_j^{(r)} \phi_i^{(s)} = 0.$$

Because of the symmetry $a_{ij} = a_{ji}$ and $b_{ij} = b_{ji}$ the quadratic forms are the same in both equations, and by subtraction of Eq. (3.9) we find that if λ_s and λ_r are distinct, this implies

$$\sum_{ij} a_{ij} \phi_j^{(s)} \phi_i^{(r)} = \sum_{ij} b_{ij} \phi_j^{(s)} \phi_i^{(r)} = 0. \quad (3.10)$$

These equations express the orthogonality of the modes. It is easily verified that they cannot be satisfied if the modes are complex conjugates because of the property that the quadratic forms are positive. So the modes are real. Moreover if we put $s=r$ in (3.9) we find

$$\lambda_s = \frac{\sum_{ij} a_{ij} \phi_i^{(s)} \phi_j^{(s)}}{\sum_{ij} b_{ij} \phi_i^{(s)} \phi_j^{(s)}} = \frac{V}{D}, \quad (3.11)$$

where V and D are positive definite forms corresponding to the potential energy V and the dissipation function D (in which we replace q_i by $\phi_i^{(s)} t$). Therefore, all roots $-\lambda_s$ are real and negative.

Now these properties are not restricted to the case where all roots are distinct, finite, and different from zero. In case of a multiple root $-\lambda_s$ of multiplicity α , we may determine α orthogonal modes corresponding to this root. Also, in the case of an infinite root we have a mode which is simply a column of constants independent of time. The case of a zero root corresponds to a solution of the type

$$q_j^{(s)} = \phi_j^{(s)} t. \quad (3.12)$$

This will be further clarified by considering the system from the standpoint of normal coordinates in the next section.

In most physical systems a great many variables are "hidden," i.e., we do not observe them. External forces are only applied to k coordinates $q_1 \cdots q_k$ while the $n-k$ others constitute what we shall call the internal system. This is expressed by writing Eqs. (3.1) in the form

$$\begin{bmatrix} N & S \\ T & M \end{bmatrix} \begin{bmatrix} q_1 \\ q_k \\ q_{k+1} \\ \vdots \\ q_n \end{bmatrix} = \begin{bmatrix} Q_1 \\ Q_k \\ 0 \\ \vdots \\ 0 \end{bmatrix}. \quad (3.13)$$

The matrix M represents an internal subsystem of $n-k$ degrees of freedom which is of the same general nature as the total system with its own $n-k$ relaxation constants σ_s and modes corresponding to roots $-\sigma_s$ of the determinant of the submatrix $[M]$,

$$M = \det[M] = 0. \quad (3.13)$$

The relaxation constants λ_s correspond to a set of relaxation times which if a great many degrees of freedom are considered may be said to constitute a spectrum. The spectrum σ_s of a subsystem will depend of course on the particular subsystem which is considered as internal. It is also a consequence of the properties of the type of matrices involved that the roots σ_s are located between the roots λ_s because the system defined by the matrix M may be considered as the original system of determinant Δ in which k restraints, $q_1 = q_2 = \cdots q_k = 0$, have been introduced.

IV. NORMAL COORDINATES AND GENERALIZED FORCES

We perform a change of coordinates from q_i to ξ_s by the n linear relations

$$q_i = \sum_s \phi_i^{(s)} \xi_s, \quad (4.1)$$

where $\phi_i^{(s)}$ is the modal column of the s th relaxation mode. The ξ_s 's are called the normal coordinates. The

Lagrangian Eq. (2.14) then becomes

$$\frac{\partial V}{\partial \xi_s} + \frac{\partial D}{\partial \dot{\xi}_s} = \Xi_s \quad (4.2)$$

where the generalized normal force Ξ_s corresponding to the coordinate ξ_s is given by

$$\Xi_s = \sum_j^i \phi_j^{(s)} Q_j. \quad (4.3)$$

We normalize the $\phi_j^{(s)}$ columns in such a way that for each s

$$\sum_{ij} b_{ij} \phi_i^{(s)} \phi_j^{(s)} = 1 \quad (4.4)$$

except for the case where $\lambda_s = \infty$ where we normalize by

$$\sum_{ij} a_{ij} \phi_i^{(s)} \phi_j^{(s)} = 1. \quad (4.5)$$

Then we may write for $\lambda_s \neq \infty$,

$$V = \frac{1}{2} \sum_s \lambda_s \xi_s^2, \quad (4.6)$$

$$D = \frac{1}{2} \sum_s \dot{\xi}_s^2$$

and for $\lambda_s = \infty$,

$$\begin{aligned} V &= \frac{1}{2} \sum_s \xi_s^2, \\ D &= 0. \end{aligned} \quad (4.7)$$

The Lagrangian equations for the normal coordinates are thus the n equations

$$\begin{aligned} (p + \lambda_s) \xi_s &= \Xi_s, \\ \xi_s &= \Xi_s, \end{aligned} \quad (4.8)$$

where the last equation corresponds to modes of infinite root λ_s . These are n equations which are quite general and may correspond to any case of multiplicity of λ_s or to zero and infinite roots. In the case of α multiplicity of a root λ_s the corresponding Eq. (4.8) is simply repeated α times.

Equations (4.8) are immediately solved in terms of the coordinates

$$\begin{aligned} \xi_s &= \frac{\Xi_s}{p + \lambda_s}, \\ \xi_s &= \Xi_s. \end{aligned} \quad (4.9)$$

With these results we may solve the fundamental Eq. (3.1) for the variables q_j in terms of the forces Q_j . Substituting ξ_s in (4.1) and using (4.3) for Ξ_s , we find

$$q_i = \sum_{j=1}^k Q_j \left[\sum_s \frac{C_{ij}^{(s)}}{p + \lambda_s} + C_{ij} \right]. \quad (4.10)$$

The summation $\sum_s$ is extended to all the *distinct* roots

λ_s .

$$C_{ij}^{(s)} = \phi_i^{(s)} \phi_j^{(s)} \quad (4.11)$$

if λ_s is a single root and

$$C_{ij}^{(s)} = \sum \phi_i^{(s)} \phi_j^{(s)} \quad (4.12)$$

is the summation extended to all the modes of the multiplicity α if λ_s is a multiple root. The value of C_{ij} is the same expression as (4.11) and (4.12) corresponding to the infinite roots, single or multiple. From these expressions it is seen that the diagonal terms $C_{ii}^{(s)}$ and C_{ii} are always positive and that the coefficients are symmetric, i.e.,

$$C_{ij}^{(s)} = C_{ji}^{(s)}, \quad C_{ij} = C_{ji}. \quad (4.13)$$

In expression (4.10) the summation is extended from $j=1$ to $j=k$ over all forces Q_j which are taken different from zero. The k first equations therefore give the observed variables q_1 and q_k in terms of the forces Q_1 to Q_k applied to those coordinates.

Now we would like to solve these equations back and express the k applied forces in terms of the observed coordinates. This is best done by going back to the original Eqs. (3.13).

We consider the subsystem represented by the equation

$$\begin{bmatrix} M \end{bmatrix} \begin{bmatrix} q_{k+1} \\ \vdots \\ q_n \end{bmatrix} = 0. \quad (4.14)$$

This system may be represented by its $n-k$ normal coordinates $\xi_{k+1} \cdots \xi_n$. The complete n degree of freedom system may be represented by these normal coordinates and by the k coordinates $q_1 \cdots q_k$. The potential energy and the dissipation function for this system may then be written

$$V = \frac{1}{2} \sum_{ij} a_{ij} q_i q_j + \sum_{is} a_{is}' q_i \xi_s + \frac{1}{2} \sum_s \sigma_s \xi_s^2, \quad (4.15)$$

$$D = \frac{1}{2} \sum_{ij} b_{ij} \dot{q}_i \dot{q}_j + \sum_{is} b_{is}' \dot{q}_i \dot{\xi}_s + \frac{1}{2} \sum_s \dot{\xi}_s^2,$$

where i and j vary from 1 to k and s from $k+1$ to n . As before we note that if one of the roots σ_s of M is infinite, the normalization of the mode can be done in such a way that the corresponding ξ_s^2 term in the dissipation function does not appear while there is a term ξ_s^2 in the potential energy. In that case, however, the condition that D is positive definite also requires that all coefficient b_{is}' corresponding to that mode vanish. Similarly since V is also positive definite if there are zero values of σ_s all corresponding coefficients a_{is}' must be zero.

With normal coordinates for the subsystem, the

equations for the complete system become

$$\begin{bmatrix} A_{11} & A_{1k} & A_{1,k+1}' & A_{1n}' \\ A_{k1} & A_{kk} & A_{k,k+1}' & A_{kn}' \\ \hline A_{k+1,1}' & A_{k+1,k}' & \beta_{k+1} & \\ \hline A_{n1}' & A_{nk}' & 0 & \beta_{nn} \end{bmatrix} \begin{bmatrix} q_1 \\ q_k \\ \xi_{k+1} \\ \xi_n \end{bmatrix} = \begin{bmatrix} Q_1 \\ Q_k \\ 0 \\ 0 \end{bmatrix}, \quad (4.16)$$

where $A_{ij} = a_{ij} + pb_{ij}$, $A_{is}' = a_{is}' + pb_{is}'$ and $\beta_s = p + \sigma_s$ or 1, depending on whether σ_s is finite or infinite. We now solve the last $n-k$ equations for ξ_s . If $\sigma_s \neq \infty$, we may write

$$\xi_s = - \sum_{j=1}^k \frac{A_{sj}' q_j}{p + \sigma_s} \quad (4.17)$$

and, if $\sigma_s = \infty$,

$$\xi_s = - \sum_{j=1}^k A_{sj}' q_j = - \sum_{j=1}^k a_{sj}' q_j. \quad (4.18)$$

We also note that, if $\sigma_s = 0$,

$$\xi_s = - \sum_{j=1}^k b_{sj}' q_j. \quad (4.19)$$

Substituting these values of ξ in the first k equations, we find

$$Q_i = \sum_j T_{ij} q_j \quad (4.20)$$

with

$$T_{ij} = A_{ij} - \sum_s \frac{A_{is}' A_{sj}'}{p + \sigma_s}. \quad (4.21)$$

If σ_s is zero or infinite for any particular mode the last term is replaced, respectively, by

$$A_{is}' A_{sj}' = A_{is}' b_{sj}', \quad (4.22)$$

$$A_{is}' A_{sj}' / p + \sigma_s = A_{is}' a_{sj}'. \quad (4.23)$$

All coefficients in (4.20) are symmetric

$$T_{ij} = T_{ji}. \quad (4.24)$$

The coefficients may be written

$$T_{ij} = \sum_s \frac{p}{p + \sigma_s} D_{ij}^{(s)} + D_{ij} + D_{ij}' p, \quad (4.25)$$

where

$$\begin{aligned} D_{ij}^{(s)} &= \psi_i^{(s)} \psi_j^{(s)}, \\ D_{ij} &= a_{ij} - \sum_s \frac{a_{is}' a_{sj}'}{\sigma_s}, \\ D_{ij}' &= b_{ij} - \sum_s b_{is}' b_{sj}', \\ \psi_i^{(s)} &= a_{is}' / \sigma_s - \sigma_s^{-1} b_{is}'. \end{aligned} \quad (4.26)$$

All diagonal terms of the matrix T_{ij} are positive. This may be seen directly from the expression (4.26) for $D_{ii}^{(s)}$. As regards D_{ii} and D_{ii}' they must be positive because the ratio Q_i/q_i and $Q_i/\dot{q}_i$ must be positive for $p=0$ and $p=\infty$, respectively. Expression (4.25) of T_{ij} shows that any relaxation phenomena may be represented by a spring, a dashpot, and a sum of a great many elements made up of a Maxwell type material corresponding to the operator

$$(p/p + \sigma_s) D_{ij}^{(s)}. \quad (4.27)$$

Such a Maxwell material is represented by a spring and dashpot in series. We thus have shown that a mechanical model of springs and dashpots in series and in parallel may represent a very wide variety of relaxation effect involving not only mechanical, but chemical, thermodynamic phenomena, etc., and coupled effects between them.

V. APPLICATION TO THE GENERAL STRESS-STRAIN RELATIONS IN AN ANISOTROPIC CONTINUUM

We shall apply the previous theory to the formulation of the stress-strain relations in a viscoelastic material or more generally to any material exhibiting relaxation effects. We assume the deformation of this material under stress to be made of the variation of many degrees of freedom both internal and external. The internal degrees of freedom may be of mechanical, chemical, or other physical nature. In this case the nine stress components

$$\sigma_{\mu\nu} = \begin{Bmatrix} \sigma_{xx} & \sigma_{xy} & \sigma_{xs} \\ \sigma_{yx} & \sigma_{yy} & \sigma_{ys} \\ \sigma_{zx} & \sigma_{zy} & \sigma_{zs} \end{Bmatrix} \quad (5.1)$$

applied to the faces of an elementary cube of material play the role of applied generalized forces $Q_1 \cdots Q_k$ ($k=9$) considered in the previous section. The nine corresponding observed coordinates $q_1 \cdots q_k$ are the nine components of the strain tensor,

$$e_{\mu\nu} = \begin{Bmatrix} e_{xx} & e_{xy} & e_{xz} \\ e_{yx} & e_{yy} & e_{yz} \\ e_{zx} & e_{zy} & e_{zs} \end{Bmatrix}. \quad (5.2)$$

Because of the symmetry

$$\sigma_{\mu\nu} = \sigma_{\nu\mu}, \quad e_{\mu\nu} = e_{\nu\mu} \quad (5.3)$$

we have only six independent components of these tensors. We now apply relations (4.20) and (4.25) to this material and write

$$\sigma_{\mu\nu} = \sum_{ij} P_{\mu\nu}^{ij} e_{ij} \quad (5.4)$$

with

$$P_{\mu\nu}^{ij} = \sum_s \frac{p D_{\mu\nu}^{ij(s)}}{p + \sigma_s} + D_{\mu\nu}^{ij} + p D_{\mu\nu}'^{ij}. \quad (5.5)$$

This is an operational tensor having the following sym-

metry properties:

$$P_{\mu\nu}^{ij} = P_{\nu\mu}^{ji} = P_{\mu\nu}^{ji}, \quad P_{\mu\nu}^{ij} = P_{ij}^{\mu\nu}. \quad (5.6)$$

These properties are the same as those of the elastic moduli of the theory of elasticity and we may therefore treat these operators in a similar way. By solving these equations with respect to the strain, we shall obtain a similar expression with an operator having the same form as in Eq. (4.10).

In expression (5.5) the summation is extended to all internal relaxation constants σ_s . Since the solid has a great many internal degrees of freedom there may be in some cases an almost continuous distribution of relaxation modes. This will correspond to a spectrum or spectral density distribution of the relaxation constant. With a density distribution function $\gamma(\sigma)$ we may write

$$P_{\mu\nu}^{ij} = p \int_0^\infty \frac{D_{\mu\nu}^{ij}(\sigma) \gamma(\sigma)}{p + \sigma} d\sigma + D_{\mu\nu}^{ij} + p D_{\mu\nu}^{'ij}. \quad (5.7)$$

This operational tensor is an analytic function of the time operator p . The more general representation of the operational tensors $P_{\mu\nu}^{ij}$ is therefore a set of 21 analytic functions of p constituting a symmetric six by six matrix. Under the integral, due account must be taken of the possibility of degeneracy of the modes in evaluating the product $D_{\mu\nu}^{ij}(\sigma) \gamma(\sigma)$. From expressions (4.26) we see that we may write

$$D_{\mu\nu}^{ij}(\sigma) = \psi_{\mu\nu}(\sigma) \psi^{ij}(\sigma). \quad (5.8)$$

VI. SPECIAL CASES OF SYMMETRY

The operational equations (5.4) may be simplified if we introduce the assumption that the material has a certain degree of symmetry. We shall discuss two examples, the case of cubic symmetry and the case of isotropy.

We proceed as in the classical theory of elasticity, where in the present case the operational tensor plays the same role as the elastic moduli. The relation between stress and strain must remain invariant under certain symmetry operations. In elasticity a cubic crystal has three elastic constants. Similarly in our case cubic symmetry leads to three operational tensor components. If we take the coordinate axes along the cubic axes the stress strain relations become

$$\begin{aligned} \sigma_{xx} &= 2Qe_{xx} + Re, \\ \sigma_{yy} &= 2Qe_{yy} + Re, \\ \sigma_{zz} &= 2Qe_{zz} + Re, \\ \sigma_{xy} &= 2Se_{xy}, \\ \sigma_{yz} &= 2Se_{yz}, \\ \sigma_{zx} &= 2Se_{zx}, \end{aligned} \quad (6.1)$$

with $e = e_{xx} + e_{yy} + e_{zz}$. The three operators are

$$\begin{aligned} Q &= \sum_s \frac{pQ^s}{p + \sigma_s} + Q + Q'p, \\ R &= \sum_s \frac{pR^s}{p + \sigma_s} + R + R'p, \\ S &= \sum_s \frac{pS^s}{p + \sigma_s} + S + S'p. \end{aligned} \quad (6.2)$$

The quantities $Q^s, Q, Q', R^s, \dots$ etc. are characteristic constants of the material, and σ_s are the internal relaxation constants. The summation may be replaced by an integration with a spectral distribution.

In the case of isotropy the number of operators is further restricted. The condition of invariance under any rotation implies

$$Q = S \quad (6.3)$$

and the stress-strain relations for the isotropic case become

$$\begin{aligned} \sigma_{xx} &= 2Qe_{xx} + Re, \\ \sigma_{yy} &= 2Qe_{yy} + Re, \\ \sigma_{zz} &= 2Qe_{zz} + Re, \\ \sigma_{xy} &= 2Qe_{xy}, \\ \sigma_{yz} &= 2Qe_{yz}, \\ \sigma_{zx} &= 2Qe_{zx}. \end{aligned} \quad (6.4)$$

The two operators Q and R are invariants of the form (6.2) and are the formal analogs of the Lamé constants in the theory of elasticity. The case of hydrostatic stress is obtained by putting

$$\sigma_{xx} = \sigma_{yy} = \sigma_{zz}, \quad (6.5)$$

$$\sigma_{xy} = \sigma_{yz} = \sigma_{zx} = 0,$$

with

$$3\sigma = \sigma_{xx} + \sigma_{yy} + \sigma_{zz}, \quad (6.6)$$

we find

$$\sigma = (\frac{2}{3}Q + R)e. \quad (6.7)$$

The operator $\frac{2}{3}Q + R$ is equivalent to a bulk modulus. The existence of this operator in the general form correspond to the assumption of bulk relaxation or volume creep. This may of course occur at high pressure or for porous materials. If $\frac{2}{3}Q + R$ is a constant, then the material obeys Hooke's law under hydrostatic pressure. Denoting by K the elastic bulk modulus this requires a relation between the operators Q and R ,

$$\frac{2}{3}Q + R = K. \quad (6.8)$$

Equations (6.4) are then expressed by means of a single operator Q ,

$$\begin{aligned} \sigma_{xx} &= 2Qe_{xx} + (K - \frac{2}{3}Q)e, \\ \sigma_{xy} &= 2Qe_{xy}. \end{aligned} \quad (6.9)$$

Very often the assumption is made that the material is

incompressible. In this case the operator R is infinite and $e=0$, but the product Re is finite and the limiting relation (6.7) is

$$\sigma = Re. \quad (6.10)$$

It is convenient to introduce this negative hydrostatic pressure σ in the relations (6.4) and write

$$\begin{aligned} \sigma_{xx} - \sigma &= 2Qe_{xx}, \\ \sigma_{yy} - \sigma &= 2Qe_{yy}, \\ \sigma_{zz} - \sigma &= 2Qe_{zz}, \\ \sigma_{xy} &= 2Qe_{xy}, \\ \sigma_{yz} &= 2Qe_{yz}, \\ \sigma_{zy} &= 2Qe_{zx}. \end{aligned} \quad (6.11)$$

In this case also a single operator Q is necessary to characterize the material.

There is need to call attention to a difference between

the operational stress-strain relations and the theory of elasticity with respect to symmetry properties. This is the possibility of occurrence of multiple or mixed symmetry. If we note that $P_{\mu\nu}^{ij}$ is written in terms of the tensor

$$D_{\mu\nu}^{ij(s)} \quad D_{\mu\nu}^{ij} \quad D'_{\mu\nu}{}^{ij}, \quad (6.12)$$

it is not contradictory to assume that each of these tensors has its own symmetry. The material would then exhibit different symmetries, each of which would predominate at various strain rates.

ACKNOWLEDGMENTS

The author is indebted to the Shell Development Company for permission to publish the present work which has been sponsored during the past years as part of a research program on the mechanical properties of rock at the Exploration and Production Research Division in Houston, Texas.